

ShaliCryl[®] TC 100 ES

UV / Weather Resistant Exterior Acrylic Silicone Top Coat



STP Limited

Description

ShaliCryl[®] TC 100 ES is single component, UV resistant exterior emulsion paint based on silicone modified acrylic polymer that provides excellent weatherability, water, dirt pickup and stain resistance.

ShaliCryl[®] TC 100 ES is easy to apply, environment friendly, non-polluting, green product, which forms a tough impermeable, breathable layer with a high crack bridging property of up to 2 mm.

ShaliCryl[®] TC 100 ES is available in white base, **which can be pigmented with accompanying paste.**

It conforms to ASTM D-6083.

Characteristics - Physical

Appearance	Viscous dispersion	Specific Gravity	1.3
Application Temperature °C	> 5	Viscosity, cps at 30 °C	2500 ± 200
UV Resistance	Excellent	Theoretical Coverage, m ² /L *	5– 6.
Vol Solid, %	60 ± 2	Dust pick up resistance	Excellent
DFT, micron	100-120	Water repellency	Excellent
Appearance after drying	Smooth film with sheen	Drying time, minutes • Surface dry • Hard dry	10 90

* Depending upon surface condition.

Characteristics - Technical

Property	Standard	Results
Elongation, 14 days, %	ASTM D6083	550 ± 50
Tensile strength, 14 days, MPa,	ASTM D6083	1.20 ± 0.1
Hardness, 14 days /Shore A	ASTM D2240	70 - 72
Gloss / Sheen level @ 60° Angle	ASTM D 523	8 - 9
Adhesion strength, MPa	ASTM D4541	1.6-2.0
Accelerated weathering (1500 hrs UV Exposure)	ASTM D 4586	No defects

Application

- As a top coat over ShaliCryl[®] 215 coating for exterior surface.

Advantages

- User friendly, Easy to clean glossy surface.
- Green elastomeric UV resistant coating.
- Excellent Dirt / Algae / Fungus Resistant.
- Excellent water repellent and lotus leaf effect.
- Excellent dust pickup / stain resistant.
- High Crack Bridging Property.
- Improves life of ShaliCryl 215 base coat.

Application Methodology

➤ Surface Preparation

- Remove all foreign materials, if any, with a jet of air from exterior surface coated with ShaliCryl 215.

➤ Application of Material

- Apply top coat of **ShaliCryl® TC 100 ES** over the prepared surface @ 160 - 200 ml / m².
- Allow the applied coating to dry for 6 – 8 hrs for post operation.
- If a second coat is required apply **ShaliCryl® TC 100 ES** without dilution over dried first coat @ 140 ml / m² and allow it to dry.
- Do not undertake any further work over the coated area within 72 hrs of final coat.

Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapor.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 5 L and 20 L container. Bulk packing is available on request.

Storage

Keep in cool and dry place, under the shade, away from heat.

Shelf Life

12 months in original unopened sealed condition.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing and Insulation ■ Road Surfacing
- Sealants and Additives ■ Pipeline Coating
- Protective / Anti-Corrosive Coating ■ Epoxy Flooring
- Grouts / Admixtures ■ RestoFix- Repair / Rehabilitation
- Other Construction Chemicals



Advisory Cell: +91 81302 81114