

ShaliFloor® WB ES 2PU

2K Water Based Polyurethane Scratch Resistant Sealer



Description

ShaliFloor® 2PU WB ES is medium hard two component water based Polyurethane coating which exhibits excellent toughness along with scratch hardness and anti-skidding properties. It can be used as a top coat for Polyurethane / Epoxy flooring.

Characteristics

Pot Life, @ 30 °C, hr	3	Surface Dry, @ 30 °C	30 – 45 Min
Density	1.02 ± 0.02	Pencil Hardness, hr	5
Theoretical Coverage*	100 – 120 gm/m ² / 2 coat on smooth surface	Tabber Abration, 1000 round, mg	26
		Appearance	Matt
		DFT in microns	30 - 40

* Depending upon surface condition.

Application

- Applied on Polyurethane and Epoxy floorings.

Advantages

- Excellent adhesion and flexibility.
- Resists scratch / abrasion / black heal mark
- Resistant to UV / weather.
- Resists chemical / normal cleaning agents used in house-keeping

Application Methodology

➤ Surface Preparation

- Prepare the surface by mechanical grinding or other suitable method.
- Remove dust, flakes, oil, grease or other loose foreign particles by sand blasting, iron brush or compressed air. Remove old painting using surface grinder.
- Remove old painting using surface grinder.
- For best bond, concrete surface must be slightly textured.
- Allow it to dry before priming.

➤ Material Preparation

- Mix **ShaliFloor® 2PU WB ES** component A (Resin) & B (Hardener) thoroughly by using speed drill mixer with a spiral type blade at the bottom of stirrer rod. The speed may be 1000 rpm till homogeneous mix is obtained.
- After stirring, wait for the product to settle in order to let entrapped air escape.

➤ Application of Material

- Prime concrete surface with ShaliPrime 2E and in case of metal surface, prime with ShaliPrime Zn R.
- Apply mixed **ShaliFloor® 2PU WB ES** on primed surface immediately by brush / trowel.

Cleaning & Maintenance

Clean tools and equipments with water.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 1 kg unit.

Storage

Store in cool dry place, under shed, away from heat.

Shelf Life

12 months in original unopened sealed conditions.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing & Insulation
- Road Surfacing
- Sealants & Adhesives
- Pipeline Coatings
- Protective/Anti-Corrosion Coatings
- Epoxy and Flooring
- Grouts and Admixtures (GARA)
- RestoFix - Repair/Rehabilitation
- Other Construction Chemicals



Advisory Cell: +91 81302 81114

www.stpltd.com

18820