

ShaliGrout® IP

Single Component Injection / Pressure Grout For Cement / Mortar / Concrete



Description

ShaliGrout® IP is a plasticized and non-shrink cement / mortar admixture for pressure / injection grouting. By introducing into the cementitious grout, it reduces water cement ratio and facilitates volume expansion without segregation or bleeding. It may also be used to get water tight dense structures. It complies with BS 8110 part 1, 1985, section 8.9.4.6.

Characteristics

Compressive Strength 50 mm cube, kg/Cm ²	Increases due to reduced water cement ratio	Setting time	Does not effect
		Chloride Content	NIL
Expansion	1 to 4% unrestrained expansion to compensate for plastic shrinkage of cement. Time for expansion will be 15 minutes to 2 hours depending on temperature		

Application

- Bed grouting.
- Pre-stressed cable duct grouting.
- Non-shrink infilling & joints at RCC hume pipes.
- Tunnel linings.
- Water Tank pressure grouting.
- Flat as well as slopping roof.
- Stationery machine foundation grouting.

Advantages

- Gaseous expansion to compensate plastic shrinkage of cement.
- Reduced w/c ratio to ensure low permeability and increased cohesion.
- Hydrophobic additives give better water tight structure.
- Free of chloride.
- Does not attack reinforcement or prestress cables.

Application Methodology

- Add **ShaliGrout® IP** @ 1 % by weight of cement for neat cement on 2 % by weight of cement in case of concrete / mortar.
- For some special case, a higher dosage may be used in consultation with STP's technical team.
- Over-dosing increases expansion and causes frothing.
- **ShaliGrout® IP** is compatible with all kinds of Portland cement, including SRC (Sulphate Resistant Cement), but is incompatible with high alumina cement. It is strongly recommended not to use **ShaliGrout® IP** with cement having high alumina content.

Health & Safety

- Use mask, nose cover and hand gloves during application.
- Clean hands with soap water after application.
- Avoid contact with skin / eyes. In case of unlikely contact with eyes, rinse immediately with plenty of clean water, then cleanse with soap and lukewarm water and seek medical advice. Do not use solvent to clean the contacted area.

- Prevent swallowing. In case of unlikely swallowing, seek medical attention immediately. Do not induce vomiting.

Packing

Available in carton containing 1 kg x 12 Nos. or in 30 kg bag.

Storage

Store in cool dry place, under the shed, away from heat.

Shelf Life

12 months in original unopened sealed conditions.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing and Insulation ■ Road Surfacing
- Sealants and Additives ■ Pipeline Coating
- Protective / Anti-Corrosive Coating ■ Epoxy Flooring
- Grouts / Admixtures ■ RestoFix- Repair / Rehabilitation
- Other Construction Chemicals



Advisory Cell: +91 81302 81114

