

ShaliPoxy[®] 400 FG

2K Food Grade Epoxy Coating For Single Feed Airless Spray Gun



Description

ShaliPoxy[®] 400 FG is fast setting, spray applied, solvent free, food grade, two component epoxy coating for internal / external lining of steel / concrete surface of pipes, vessels and other equipment used for potable water. **ShaliPoxy[®] 400 FG** is **spray** applied by single feed airless spray gun.

ShaliPoxy[®] 400 FG may be designed to meet specific physical and / or technical characteristics parameters required by the customer. The undernoted physical and / or technical parameters are of standard **ShaliPoxy[®] 400 FG** produced by the company.



It conforms to BS : 6920 : 2014, IS 16676:2017 (Clauses 4.3 & 9.1) and AWWA C-210 : 2003.

Characteristics – Physical

Appearance of Resin	Viscous colored Liquid	Appearance of Hardener	Viscous Brown Liquid
Pot Life @ 27 °C, 55% RH, 100 gm, minute	60 ± 10	Theoretical Coverage *, m ² / L, 200 Micron DFT	4.2
Drying time, @ 27 °C, 55% RH <ul style="list-style-type: none">• Touch dry, hrs• Hard dry, hrs• Full cure, days	3	Volume Solids, %	85 ± 5
	6 – 8	Mixing Ratio, by volume	3:1
	7	Application Temp, °C with RH < 75%	10 - 50

* Depending upon surface condition

Characteristics - Technical

Tensile strength, MPa	ASTM D 638	12 ± 2
Abrasion Resistance, 1000 cycle	ASTM D 4060	< 100 mg
Adhesion pull-off, MPa <ul style="list-style-type: none">• On concrete• On Steel	ASTM D 4541	> 3 > 10
Elongation, %	ASTM D 638	3 ± 1
Water vapor transmission, 24 hrs, gm / m ²	ASTM E 96	0.10
Hardness, Shore D	ASTM D 2240	70 ± 5
Immersion test, 30 days <ul style="list-style-type: none">• DIW• 1% H₂SO₄• 1% NaOH	AWWA C 210	No blistering / peeling / disbanding
Long term contact with potable water for human consumption	NSF/ANSI 61	No effect
Scratch Resistance, 1.5 kg load	IS:101	No failure
Compressive Strength (MPa)	ASTM C 109	50 ± 10
Salt spray test, 5000 hrs	ASTM B 117	Passes
Dielectric Strength, V / mil	ASTM D 149	250
Cathodic Disbondment, mm	ASTM G 8	6.5

Application

- Excellent coating for internal / external lining of pipelines where abrasion / chemical resistance is of major concern.
- Excellent coating for internal / external linings of potable water pipelines.
- Internal coating for concrete / steel potable water storage.
- Sea water intake tunnels.

Advantages

- Solvent free, fast setting, high build-up epoxy.
- Excellent film built capabilities exceeding 200 Micron in single coat, which can be extended with multiple passes.
- Excellent food grade properties.
- Excellent chemical / abrasion resistance properties.
- Good temperature resistance properties.
- Very low permeability.

Application Methodology

➤ Surface Preparation

- Remove all loose gravel, dirt, oil, grease or other loose foreign particles by sand blasting / iron brush / compressed air.
- Prepare surface by mechanical grinding, shot blasting conforming to SA2½.

➤ Material Preparation

- Stir drums of each component thoroughly for uniformity. For best result, use a variable speed drill mixer with a spiral type blade at the bottom of stirrer rod. The speed may be 400-600 rpm.

➤ Application of Material

- Apply **ShaliPoxy® 400 FG** by single feed airless spray gun to the required thickness on the prepared substrate to achieve 200 to 300 Micron / coat.
- The tip pressure typically should be 2500-4000 psi (the tip pressure should be adjusted to achieve good atomization of the spray).
- Tip size typically should be 27 - 35 Thou orifice.

Cleaning & Maintenance

Clean all tools immediately after use with STPThinner E.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 20 L drum consisting of Component A 15 L and Component B 5 L.

Storage

Store in a cool dry place, under shade, away from heat.

Shelf Life

12 months in original, unopened, sealed condition.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing and Insulation
- Road Surfacing
- Sealants and Additives
- Pipeline Coating
- Protective / Anti-Corrosive Coating
- Epoxy Flooring
- Grouts / Admixtures
- RestoFix- Repair / Rehabilitation
- Other Construction Chemicals



Advisory Cell: +91 81302 81114